TECHNICAL DATA SHEET

OKBE10638

3 Ply 225 Tan Puregum Roughtop x Bare
225 PIW

ORIONTEK
ENGINEERING GOOD SOLUTIONS

01 CONSTRUCTION

TOP COVER	Compound	Tan NR
	Surface	Roughtop
	Colour	Tan
CARCASS	Fabric	Polyester
	Number of plies	3
	Cross rigid	No
BOTTOM	Compound	Bare RFL
	Surface	Bare

02 TECHNICAL SPECIFICATIONS

Overall gauge	**5/16**	in.	*7.94*	*mm*
Unit weight	**0.1340**	lb/PIW		
Tension rating	**225**	PIW	*39.4*	*N/mm*
Temperature – minimum [1]	**–40**	°F	*–40*	*°C*
Temperature – maximum [1]	**250**	°F	*121*	*°C*

03 MINIMUM PULLEY DIAMETER [2]

Minimum pulley diameter	**8.00 in**





CROSS-SECTION – NOT TO SCALE

GAUGE 5/16 IN. / 7.94 MM

04 PROPERTIES

FDA compliant compound	NO
Oil resistant	NO
Fire resistant	NO
High heat	NO
Static conducting	NO
Cross rigid	NO
Impression (textured) top	YES

05 SPLICING & FASTENERS

Step splice	Yes
Finger splice	No
Staple fastener	#125
Wire hook lacing	#1
Alligator lacing	#7

06 APPLICATION

The tan color is non-marking. The genuine gum is a soft durometer for the highest grab, steepest inclines and long wear where required. The bare bottom construction is popular for surface finishing machinery applications.

Oriontek service: supplied endless-joined, open-length or fabricated with profiles, sidewalls, cleats and V-guides. Onsite splicing available.

NOTES [1] Operating the belt at its limit values may reduce service life. [2] Minimum pulley diameters depend on belt tension and on the splice or fastener specified by Oriontek. All values are nominal.

DISCLAIMER Values are nominal. They describe the product as tested and do not necessarily reflect conditions of industrial use, nor do they guarantee suitability for a specific application. The customer remains responsible for correct selection and use. Oriontek cannot be held liable for damages arising from use of this product. Specifications may be revised without prior notice.