TECHNICAL DATA SHEET

OKBE10708

5 Ply Poly 225 Blk Heavy Duty Nitrile FBS
Oil resistant · 225 PIW

ORIONTEK
ENGINEERING GOOD SOLUTIONS

01 CONSTRUCTION

TOP COVER	Compound	Polyester
	Surface	Friction Surface
	Colour	Black
CARCASS	Fabric	Polyester
	Number of plies	5
	Cross rigid	No
BOTTOM	Compound	Polyester
	Surface	Friction Surface


02 TECHNICAL SPECIFICATIONS

Overall gauge	11/64	in.	4.37	mm
Unit weight	0.0940	lb/PIW		
Tension rating	225	PIW	39.4	N/mm
Temperature — minimum [1]	0	°F	-18	°C
Temperature — maximum [1]	250	°F	121	°C

03 MINIMUM PULLEY DIAMETER [2]

Minimum pulley diameter	3.00 in





FABRIC TOP FACE
friction surface · black

5-PLY POLYESTER
polyester

FABRIC DRIVE FACE
friction surface · drive sid

CROSS-SECTION — NOT TO SCALE

GAUGE 11/64 IN. / 4.37 MM

04 PROPERTIES

FDA compliant compound	NO
Oil resistant	YES
Fire resistant	NO
High heat	NO
Static conducting	NO
Cross rigid	NO
Impression (textured) top	NO

05 SPLICING & FASTENERS

Step splice	Yes
Finger splice	No
Wire hook lacing	#3
Alligator lacing	#20

06 APPLICATION

These belts are recommended for handling metal stampings, automotive parts, sheet steel and any application requiring very high oil resistance. Features rugged, high-strength polyester carcass; suitable for medium-capacity transmission belt where oil, grease or chemicals are present. Flexible, yet will withstand cutting, gouging and abrasion.

Oriontek service: supplied endless-joined, open-length or fabricated with profiles, sidewalls, cleats and V-guides. Onsite splicing available.

NOTES [1] Operating the belt at its limit values may reduce service life. [2] Minimum pulley diameters depend on belt tension and on the splice or fastener specified by Oriontek. All values are nominal.

DISCLAIMER Values are nominal. They describe the product as tested and do not necessarily reflect conditions of industrial use, nor do they guarantee suitability for a specific application. The customer remains responsible for correct selection and use. Oriontek cannot be held liable for damages arising from use of this product. Specifications may be revised without prior notice.