TECHNICAL DATA SHEET

OKBE50183

1 Ply 330 3/16in x 1/16in Straight Warp
330 PIW

ORIONTEK
ENGINEERING GOOD SOLUTIONS

01 CONSTRUCTION

TOP COVER	Compound			**Black SBR**
	Thickness	**3/16** in.	*4.76* *mm*	
	Surface			**Smooth**
	Colour			**Black**
CARCASS	Fabric			**Poly/Nylon**
	Number of plies			**1**
BOTTOM	Compound			**Black SBR**
	Thickness	**1/16** in.	*1.59* *mm*	
	Surface			**Smooth**





TOP COVER black · smooth
1-PLY POLY/NYLON poly/nylon
BOTTOM COVER smooth · drive side

CROSS-SECTION — NOT TO SCALE

GAUGE 3/8 IN. / 9.52 MM

02 TECHNICAL SPECIFICATIONS

Overall gauge	**3/8**	in.	*9.52*	*mm*
Unit weight	**0.2170**	lb/PIW		
Tension rating	**330**	PIW	*57.7*	*N/mm*
Temperature — minimum [1]	**–13**	°F	*–25*	*°C*
Temperature — maximum [1]	**176**	°F	*80*	*°C*

03 MINIMUM PULLEY DIAMETER [2]

■ Head pulley @ 80–100% tension	**18.00**	in.	*457.20*	*mm*
■ Head pulley @ 60–79% tension	**16.00**	in.	*406.40*	*mm*
■ Head pulley @ ≤59% tension	**14.00**	in.	*355.60*	*mm*
■ Tail pulley	**14.00**	in.	*355.60*	*mm*

04 SPLICING & FASTENERS

Splice process	**Finger**
Step size	**0.00 in.**
Plate / rivet fastener	**R5**

Oriontek service: supplied endless-joined, open-length or fabricated with profiles, sidewalls, cleats and V-guides. Onsite splicing available.

NOTES [1] Operating the belt at its limit values may reduce service life. [2] Minimum pulley diameters depend on belt tension and on the splice or fastener specified by Oriontek. All values are nominal.

DISCLAIMER Values are nominal. They describe the product as tested and do not necessarily reflect conditions of industrial use, nor do they guarantee suitability for a specific application. The customer remains responsible for correct selection and use. Oriontek cannot be held liable for damages arising from use of this product. Specifications may be revised without prior notice.