TECHNICAL DATA SHEET

OKCHC181

elastomer conveyor belt · Blue gp · 6.50 mm
High-friction conveying surface · Antistatic

ORIONTEK
ENGINEERING GOOD SOLUTIONS

Manufactured in Europe to Oriontek specification. Supplied, fabricated and installed by Oriontek.

01 CONSTRUCTION


CONVEYING	Material			**Synthetic elastomer**
	Thickness	**3.00** mm	*0.118* *in.*	
	Surface pattern			**GP**
	Colour			**Blue**
	Coefficient of friction			**HF — high friction**
CARCASS	Material			**Polyamide (PA)**
DRIVING	Material			**Synthetic elastomer**
	Thickness	**0.20** mm	*0.008* *in.*	
	Surface pattern			**FL**
	Colour			**Black**


02 TECHNICAL SPECIFICATIONS

Total thickness	**6.50**	mm	*0.26*	*in.*
Weight	**6.00**	kg/m²	*1.22*	*lbs/sq.ft*
Elongation at 1%	**7.5**	N/mm	*43.0*	*lbs/in.*
Max. admissible pull	**15**	N/mm	*85.7*	*lbs/in.*
Temperature — minimum (1)	**–20**	°C	*–4*	*°F*
Temperature — maximum (1)	**100**	°C	*212*	*°F*
Max. production width (3)	**500**	mm	*20*	*in.*

03 FRICTION — DRIVING SURFACE

Raw steel sheet	**0.20** [-]
Laminated plastic / wood	**0.25** [-]
Steel roller	**0.20** [-]
Rubberized roller	**0.30** [-]





CROSS-SECTION — NOT TO SCALE — **TOTAL 6.50 MM / 0.26 IN.**

04 PERFORMANCE & HANDLING

Humidity influence	YES
Suitable for metal detector	NO
Permanently antistatic, dynamic (UNI EN ISO 21179)	YES
Static conductivity (UNI EN ISO 284)	NO
Conveying on skid bed	NO
Conveying on rollers	YES
Skid bed on top *and* return	NO
Troughed conveying	NO
Curved conveyor	NO
Swan-neck conveying	NO
Inclined conveying	YES
Accumulation belts	NO
Chemical resistance rating	7

05 COMPLIANCE

- REACH EC 1907/2006 and amendments

06 APPROVED APPLICATIONS

- Corrugated carton — folding

Oriontek service: supplied endless-joined, open-length or fabricated with profiles, sidewalls, cleats and V-guides. Onsite splicing available.

NOTES (1) Operating the belt at its limit values may reduce service life. (2) Minimum radius and diameter values depend on the joint type specified by Oriontek. (3) Maximum production width 500 mm / 20 in.; wider widths require prior authorization.

DISCLAIMER Values are laboratory results measured at +23 °C and 50% relative humidity. They describe the product as tested and do not necessarily reflect conditions of industrial use, nor do they guarantee suitability for a specific application. The customer remains responsible for correct selection and use. Oriontek cannot be held liable for damages arising from use of this product. Specifications may be revised without prior notice.