TECHNICAL DATA SHEET

OKFOC-SPONGE-RUBBER

Cellular rubber timing belt coating · Orange foam, open cell

ORIONTEK
ENGINEERING GOOD SOLUTIONS


01 CONSTRUCTION

TOP COVER	Material		**Cellular rubber**
	Thickness	**10.0** mm	*0.394 in.*
	Surface		**Foam, open cell**
	Colour		**Orange**
CARCASS	Fabric		**PU timing belt (backing coating)**

02 TECHNICAL SPECIFICATIONS

Temperature — minimum [1]	**–40** °C	*–40* °F
Temperature — maximum [1]	**70** °C	*158* °F





CROSS-SECTION — NOT TO SCALE

03 APPLICATION

Coating thickness 10.0-20.0 mm, density 250 kg/m³. Applied to PU timing belts as a grip, cushioning or release backing.

Oriontek service: supplied endless-joined, open-length or fabricated with profiles, sidewalls, cleats and V-guides. Onsite splicing available.

NOTES [1] Operating the belt at its limit values may reduce service life. [2] Minimum pulley diameters depend on belt tension and on the splice or fastener specified by Oriontek.

DISCLAIMER Values are nominal. They describe the product as tested and do not necessarily reflect conditions of industrial use, nor do they guarantee suitability for a specific application. The customer remains responsible for correct selection and use. Oriontek cannot be held liable for damages arising from use of this product. Specifications may be revised without prior notice.