TECHNICAL DATA SHEET

OKHBFNI-5EIWH-P1

2-ply polyester food-grade conveyor belt · White impregnated fabric · 0.95 mm
Antistatic · FDA compliant compound

ORIONTEK
ENGINEERING GOOD SOLUTIONS

01 CONSTRUCTION


TOP COVER	Material	**Polyester fabric**
	Surface	**Impregnated fabric**
	Colour	**White**
CARCASS	Fabric	**Polyester (PET)**
	Number of plies	**2**
BOTTOM	Material	**Polyester fabric**
	Surface	**Impregnated fabric**
	Colour	**White**


02 TECHNICAL SPECIFICATIONS

Total thickness	**0.95**	mm	*0.037*	*in.*
Weight			**0.85 kg/m²**	
Load at 1% elongation	**4.6**	N/mm	*26.3*	*lbs/in.*
Temperature – minimum (1)	**–40**	°C	*–40*	*°F*
Temperature – maximum (1)	**110**	°C	*230*	*°F*
Max. production width	**4000**	mm	*157*	*in.*
Coefficient of friction			**Drive side on steel 0.15**	

03 MINIMUM PULLEY DIAMETER (2)

■ Minimum pulley / nose bar	**15**	mm	*0.59*	*in.*
■ Back-flex (counter-bending) pulley	**20**	mm	*0.79*	*in.*





FABRIC TOP FACE — impregnated fabric · white
2-PLY POLYESTER — polyester (pet)
FABRIC DRIVE FACE — impregnated fabric · drive s

CROSS-SECTION — NOT TO SCALE

TOTAL 0.95 MM / IN.

04 PROPERTIES

Antistatic	**YES**
FDA compliant compound	**YES**
EU 10/2011	**YES**
Halal	**YES**
Metal detector friendly	**YES**
Slider bed	**YES**
Roller bed	**YES**

05 APPLICATION

Features: Easy release, High temperature resistant, Hydrolysis resistant, Low friction running side, No stick-slip effect. Typical uses: Accumulation belt, Diverting belt, Food processing/conveying belt, Packaging belt, Transfer belt. Industries: Baked snacks, Biscuit and Crackers, Bread, Chocolate, Convenience food, Pastry, Primary food packaging. Admissible tensile force 11 N/mm. Knife-edge radius 2 mm.

Oriontek service: supplied endless-joined, open-length or fabricated with profiles, sidewalls, cleats and V-guides. Onsite splicing available.

NOTES (1) Operating the belt at its limit values may reduce service life. (2) Minimum pulley diameters depend on belt tension and on the splice or fastener specified by Oriontek.

DISCLAIMER Values are nominal. They describe the product as tested and do not necessarily reflect conditions of industrial use, nor do they guarantee suitability for a specific application. The customer remains responsible for correct selection and use. Oriontek cannot be held liable for damages arising from use of this product. Specifications may be revised without prior notice.