TECHNICAL DATA SHEET

OKHBHNU-8P

2-ply polyamide conveyor belt · Green glossy · 1.00 mm

ORIONTEK
ENGINEERING GOOD SOLUTIONS

01 CONSTRUCTION

TOP COVER	Material	**Polyamide**
	Surface	**Glossy**
	Colour	**Green**
CARCASS	Fabric	**Polyamide (PA)**
	Number of plies	**2**
BOTTOM	Material	**Polyamide**
	Surface	**Glossy**
	Colour	**Green**

02 TECHNICAL SPECIFICATIONS

Total thickness	**1.00**	mm	*0.039*	*in.*
Weight			**1.0 kg/m²**	
Load at 1% elongation	**2.0**	N/mm	*11.4*	*lbs/in.*
Temperature — minimum (1)	**−20**	°C	*−4*	*°F*
Temperature — maximum (1)	**100**	°C	*212*	*°F*
Max. production width	**1140**	mm	*45*	*in.*
Coefficient of friction			**Drive side on steel 0.15**	

03 MINIMUM PULLEY DIAMETER (2)

■ Minimum pulley / nose bar	**50**	mm	*1.97*	*in.*
■ Back-flex (counter-bending) pulley	**50**	mm	*1.97*	*in.*





FABRIC TOP FACE — glossy · green
2-PLY POLYAMIDE — polyamide (pa)
FABRIC DRIVE FACE — glossy · drive side

CROSS-SECTION — NOT TO SCALE

TOTAL 1.00 MM / IN.

04 PROPERTIES

Metal detector friendly	**YES**
Slider bed	**YES**
Roller bed	**YES**
Troughed	**YES**

05 APPLICATION

Features: Abrasion resistant on both sides, Cut resistant, Oil resistant. Typical uses: Processing belt. Industries: Various industries. Admissible tensile force 10 N/mm.

Oriontek service: supplied endless-joined, open-length or fabricated with profiles, sidewalls, cleats and V-guides. Onsite splicing available.

NOTES (1) Operating the belt at its limit values may reduce service life. (2) Minimum pulley diameters depend on belt tension and on the splice or fastener specified by Oriontek.

DISCLAIMER Values are nominal. They describe the product as tested and do not necessarily reflect conditions of industrial use, nor do they guarantee suitability for a specific application. The customer remains responsible for correct selection and use. Oriontek cannot be held liable for damages arising from use of this product. Specifications may be revised without prior notice.

SOLUTIONS@ORIONTEK.US · 786-440-6995 · ORIONTEK.US